

November 10, 2011

Attn. Scot Linkletter  
Maine Woods Pellet Company LLC  
164 Harmony Road  
Athens Maine 04912

Dear Scot,

Listed below are the results of testing a single bag of pellets dated 10/17/2011 per your request.

MC Dry basis (%); ASTM D4442, Method A:	6.03
MC Wet basis (%); ASTM E871:	5.68
Energy Value; Btu/lb; Parr 6200:	
As Received :	8258.60
Moisture Free :	8756.32
Moisture and Ash Free (MAF):	8799.41
Ash (%); Tappi 211, 525 C:	0.46
Dimensions:	
Over 1.5 in long; (%):	0
Max Length (in):	0.892
Diameter Range (in):	0.234 - 0.274
Diameter Average (in):	0.261
> 0.001" out of round (%):	60
Durability; 10 minute, 60 RPM; (%):	98.56
Fines; (1/8 inch mesh, mild agitation); (%):	0.10
Bulk Density; (Small box); [PCF]:	39.08
Bag Weight Stated (lb):	40
Bag Weight Actual (Avg. of 3 readings) (lb):	41.07

Prepared by: 

R. W. Rice, Ph.D  
Professor of Wood Science  
University of Maine  
207-581-2883

